



## EUREKANOL 50M ( NONYLPHENOL ETHOXYLATE FREE )

### COMPOSITION :

EUREKANOL 50M IS REACTIVE SULFITED MARINE OIL BASED FAT LIQUOR WITH VERY GOOD STABILITY THAT CAN BE USED TO OPEN UP WRINKLES IN THE PICKLING. EUREKANOL 50M WILL PROVIDE EXCEPTIONAL SOFTNESS TO LEATHER AND WILL PROVIDE VERY PLEASANT FEEL TO THE GRAIN SURFACE WITHOUT ANY SPEW IN THE WINTER. EUREKANOL 50M WILL NOT GIVE OFF OFFENDING ODOUR UPON AGEING. EUREKANOL 50M CAN BE BLENDED WITH OTHER FATLIQUOR TO IMPROVE STABILITY.

### APPLICATION :

- A. OPENING OF WRINKLES ALONG NECK AREA OF GOATSKIN, BUFFALO, AND HEAVY BULL HIDES
- B. RETANNING, NEUTRALIZING, AND FATLIQUORING BATH
- C. STABILIZER FOR OTHER FATLIQUORS
- D. REMOVING OF STICKY FAT ON THE LEATHER SURFACE, RESULTS FROM INSUFFICIENT STABILITY OF FATLIQUOR.
- E. UPHOLSTERY LEATHER
- F. NAPPA AND GARMENT LEATHER
- G. GLOVING LEATHER
- H. FOR WATER PROOFING LEATHER, EUREKANOL 50M WILL REACT WITH CATIONIC CHARGE METALS SUCH AS CHROME, ALUMINUM, OR ZIRCONIUM AND FORM SOAPS WITH GOOD WATER PROOFING PROPERTIES.

### PROPERTIES :

APPEARANCE :	LIGHT BROWN VISCOUS LIQUID
ANALYSIS :	pH 6.0 - 7.5
ACTIVE INGREDIENT :	80 - 83%
STABILITY:	PICKLING, RETANNING, NEUTRALIZING, AND FATLIQUORING BATH.
IONIC CHARGE :	ANIONIC

**PACKING :** 120 KGS OR 150 KGS IN RECONDITIONED PLASTIC DRUM



## EUREKANOL 50M

## P-2

<b>PICKLING OF</b>	50%	<b>WATER 25C</b>	
<b>GARMENT LEATHER :</b>	10 %	<b>SALT</b>	
	1%	<b>ALTAN MS</b>	20'
	1%	<b>FORMIC ACID ( 1: 4 )</b>	20'
	.75%	<b>GT - 50 ( 1: 4 )</b>	30'
	0.6%	<b>SULFURIC ACID</b>	
		<b>( 1:10 )</b>	60' pH 3.2 - 3.4
	.5%	<b>EUREKANOL 50M ( 1:4 )</b>	30'
	.5%	<b>EUREKANOL 50M ( 1:4 )</b>	30'
	.5%	<b>EUREKANOL 50M ( 1:4 )</b>	90'

OVER NIGHT, EVERY 120' RUN 20' TILL MORNING AND NEXT DAY CARRY CHROME TANNING AS USUAL

FOR SHOE UPPER, THE SAME PICKLING COULD BE USED

### RECHROMING OF GARMENT,UPHOLSTERY GRAIN AND SPLITS :

<b>WASHING :</b>	200%	<b>WATER 35C</b>	
	3%	<b>ALCHEM CSAM</b>	40 - 60', UNTIL SOFT
<b>DRAIN &amp; WASH :</b>	100%	<b>WATER 35C</b>	10'
<b>NEW FLOAT :</b>	100%	<b>WATER 35C</b>	
	1%	<b>EUREKANOL 50M</b>	20'
	1%	<b>EUREKANOL 50M</b>	20'
	4%	<b>CHROME 33 BASIC.</b>	
	1.5%	<b>ALTAN MS</b>	60'
	3%	<b>SODIUM ACETATE</b>	120'

OVER NIGHT, DURING THE NIGHT RUN 10' EVERY 120'

NEXT MORNING PROCEED AS USUAL

### RECHROMING OF SHOE UPPER :

<b>WASHING :</b>	100%	<b>WATER 35C</b>	
	3%	<b>ALCHEM CSA</b>	40 - 60' UNTIL SOFT
<b>DRAIN &amp; WASH :</b>	100%	<b>WATER 35C</b>	10'
<b>RECHROMING :</b>	50 - 100%	<b>WATER 45C</b>	
	1%	<b>EUREKANOL 50M</b>	30'
	3 - 5%	<b>CHROME 33 BASIC.</b>	
	1.5%	<b>ALTAN MS</b>	30'
	4%	<b>SODIUM ACETATE</b>	120'

THEN CARRY ON AS USUAL :