



EUREKANOL SFO (NONYLPHENOL ETHOXYLATE FREE)

COMPOSITION :

EUREKANOL SFO IS BLENDED SULFITED MARINE OIL BASED FATLIQUOR WITH GOOD STABILITY AND SOFTENING POWER. EUREKANOL SFO LEAVES LOW FISHY ODOUR TO LEATHER AFTER DRIED. EUREKANOL SFO WILL NOT SPEW IN THE WINTER AND WILL IMPART LIGHT FEEL TO LEATHER.

APPLICATION :

- A. RETANNING, NEUTRALIZING, AND FATLIQUORING BATH
- B. STABILIZER FOR OTHER FATLIQUORS
- C. UPHOLSTERY LEATHER
- D. NAPPA AND GARMENT LEATHER
- E. GLOVING LEATHER
- F. FOR WATER PROOFING LEATHER, EUREKANOL SFO WILL REACT WITH CATIONIC CHARGE METALS SUCH AS CHROME, ALUMINUM, OR ZIRCONIUM AND FORM SOAPS WITH GOOD WATER PROOFING PROPERTIES.

PROPERTIES :

APPEARANCE :	DARK BROWN VISCOUS PASTE
ACTIVE INGREDIENT :	52 - 57%
STABILITY :	RETANNING, NEUTRALIZING, AND FATLIQUORING BATH.
IONIC CHARGE :	ANIONIC

PACKING : 120 KGS OR 150 KGS IN RECONDITIONED PLASTIC DRUM



EUREKANOL SFO P-2

RECHROMING OF GARMENT,UPHOLSTERY GRAIN AND SPLITS :

WASHING :	200%	WATER 35C	
	3%	ALCHEM CSAM	40 - 60', UNTIL SOFT
DRAIN & WASH :	100%	WATER 35C	10'
NEW FLOAT :	100%	WATER 35C	
	1%	EUREKANOL SFO	20'
	1%	EUREKANOL SFO	20'
	4%	CHROME 33 BASIC.	
	1.5%	ALTAN MS	60'
	3%	SODIUM ACETATE	120'

OVER NIGHT, DURING THE NIGHT RUN 10' EVERY 120'

NEXT MORNING PROCEED AS USUAL

RECHROMING OF SHOE UPPER :

WASHING :	100%	WATER 35C	
	3%	ALCHEM CSAM	40 - 60' UNTIL SOFT
DRAIN & WASH :	100%	WATER 35C	10'
RECHROMING :	50 - 100%	WATER 45C	
	1%	EUREKANOL SFO	30'
	3 - 5%	CHROME	
	1.5%	ALTAN MS	30'
	4%	SODIUM ACETATE	120'

THEN CARRY ON AS USUAL: