



# EUREKANOL 821 ( APEO FREE FATLIQUOR )

## COMPOSITION :

EUREKANOL 821 IS REACTIVE SULFITED OIL WITH VERY GOOD LIGHT FASTNESS, STABILITY, AND CAN BE USED TO OPEN UP WRINKLES IN THE PICKLING.

EUREKANOL 821 WILL PROVIDE EXCEPTIONAL SOFTNESS TO LEATHER AND WILL PROVIDE VERY PLEASANT FEEL TO THE GRAIN SURFACE WITHOUT ANY SPEW IN THE WINTER.

## APPLICATION :

- A. OPENING OF WRINKLES ALONG NECK AREA OF GOATSKIN, BUFFALO, AND HEAVY BULL HIDES
- B. RETANNING, NEUTRALIZING, AND FATLIQUORING BATH
- C. STABILIZER FOR OTHER FATLIQUORS
- D. REMOVING OF STICKY FAT ON THE LEATHER SURFACE, RESULTS FROM INSUFFICIENT STABILITY OF FATLIQUOR.
- E. UPHOLSTERY LEATHER
- F. NAPPA AND GARMENT LEATHER
- G. GLOVING LEATHER
- H. FOR WATER PROOVING LEATHER, EUREKANOL 821 WILL REACT WITH CATIONIC CHARGE METALS SUCH AS CHROME, ALUMINUM, OR ZIRCONIUM AND FORM SOAPS WITH GOOD WATER PROOVING PROPERTIES.
- I. LIGHT AND PASTEL SHADES WHERE SULFITED FISH OIL CANNOT BE USED

## PROPERTIES :

APPEARANCE :	LIGHT BROWN VISCOUS PASTE
ANALYSIS :	pH 5.5 - 6.5
ACTIVE INGREDIENTS :	71 - 73%
STABILITY:	PICKLING, RETANNING, NEUTRALIZING, AND FATLIQUORING BATH.
IONIC CHARGE:	ANIONIC

**PACKING :** 120 - 150 KG RECYCLED PLASTIC DRUMS



## EUREKANOL 821 ( APEO FREE FATLIQUOR )

P-2

PICKLING OF	50	WATER 25C	
GARMENT LEATHER :	10 %	SALT	
	1%	ALTAN MS	20'
	1%	FORMIC ACID ( 1: 4 )	20'
	.75%	GT - 50 ( 1: 4 )	30'
	0.6%	SULFURIC ACID	
		( 1:10 )	60' pH 3.2 - 3.4
	.5%	EUREKANOL 821 ( 1:4 )	30'
	.5%	EUREKANOL 821 ( 1:4 )	30'
	.5%	EUREKANOL 821 ( 1:4 )	90'

OVER NIGHT, EVERY 120' RUN 20' TILL MORNING AND NEXT DAY CARRY CHROME TANNING AS USUAL

FOR SHOE UPPER, THE SAME PICKLING COULD BE USED

### RECHROMING OF GARMENT,UPHOLSTERY GRAIN AND SPLITS :

WASHING :	200%	WATER 35C	
	3%	ALCHEM CSA	40 - 60', UNTIL SOFT
DRAIN & WASH :	100%	WATER 35C	10'
NEW FLOAT :	100%	WATER 35C	
	1%	EUREKANOL 821	20'
	1%	EUREKANOL 821	20'
	4%	CHROME 33 BASIC.	
	1.5%	ALTAN MS	60'
	3%	SODIUM ACETATE	120'

OVER NIGHT, DURING THE NIGHT RUN 10' EVERY 120'

NEXT MORNING PROCEED AS USUAL

### RECHROMING OF SHOE UPPER :

WASHING :	100%	WATER 35C	
	3%	ALCHEM CSA	40 - 60' UNTIL SOFT
DRAIN & WASH :	100%	WATER 35C	10'
RECHROMING :	50 - 100%	WATER 45C	
	1%	EUREKANOL 821	30'
	3 - 5%	CHROME 33 BASIC.	
	1.5%	ALTAN MS	30'
	4%	SODIUM ACETATE	120'

THEN CARRY ON AS USUAL :